

Foam glass aggregate Installation Guide



- 1 Foam glass aggregate is typically delivered in 1.5m³ bulk bags.
- 2 Install 120-150gm/m² or similar approved separation membrane which is to be wrapped up the edges of the completed aggregate installation.
- 3 Roughly distribute aggregate around floor area.
- 4 Aggregate is light and can easily be distributed with wheelbarrows.
- 5 Even out roughly with shovel
- 6 Rake out to evenly.
- 7 Finally, aggregate should be compacted using a medium sized wacker plate.

Following compaction, boarding should be used to prevent disturbance of the aggregate.

Thickness guide for pre and post compaction.

Loose (mm)	Compacted (mm)
195	160
260	200
390	300
455	350
520	400
585	450